

Supporting Information for

A Facile and Template-Free One Pot Synthesis of Mn₃O₄ Nanostructures as Electrochemical Supercapacitors

Zhenjun Qi¹, Adnan Younis^{1,*}, Dewei Chu*, Sean Li

School of Materials Science and Engineering, University of New South Wales, Sydney, 2052, NSW, Australia

¹Equal Contribution

*Corresponding authors. E-mail: a.younis@unsw.edu.au, d.chu@unsw.edu.au

Table 1 The mass of different Mn₃O₄ samples

Sample-Name	Mass in (mg)
Mn(0.01@30)	0.88
Mn(0.05@30)	1.21
Mn(0.1@30)	0.89
Mn(0.01@60)	1.06
Mn(0.05@60)	0.94
Mn(0.1@60)	1.13
Mn(0.05@30)/carbon foam	1.10

Table 2 The variation in specific capacitance values of Mn(0.05@30) with different current densities

Current Density (A g⁻¹)	Specific Capacitance (F g⁻¹)
0.5	210
1.0	185
2.0	154
3.0	131
4.0	104.58
5.0	86.43




Fig. S1 Charge-discharge curve of pristine carbon foam