



Cite as

Nano-Micro Lett.

(2020) 12:133

Received: 25 March 2020

Accepted: 10 April 2020

© The Author(s) 2020

Bismuth-Based Free-Standing Electrodes for Ambient-Condition Ammonia Production in Neutral Media

Ying Sun^{1,2}, Zizhao Deng¹, Xi-Ming Song³, Hui Li¹, Zihang Huang¹, Qin Zhao¹, Daming Feng¹, Wei Zhang³, Zhaoqing Liu⁴, Tianyi Ma² ✉


✉ Tianyi Ma, Tianyi.Ma@newcastle.edu.au

¹ Institute of Clean Energy Chemistry, Key Laboratory for Green Synthesis and Preparative Chemistry of Advanced Materials, College of Chemistry, Liaoning University, Shenyang 110036, People's Republic of China² Discipline of Chemistry, University of Newcastle, Callaghan, NSW 2308, Australia³ Key Laboratory for Green Synthesis and Preparative Chemistry of Advanced Materials, College of Chemistry, Liaoning University, Shenyang 110036, People's Republic of China⁴ School of Chemistry and Chemical Engineering, Guangzhou Key Laboratory for Environmentally Functional Materials and Technology, Guangzhou University, Guangzhou 510006, People's Republic of China

HIGHLIGHTS

- The Bi₂O₃ nanoplates homogeneously decorated free-standing exfoliated graphene (Bi₂O₃/FEG) was prepared by a facile electrochemical deposition method.
- The Bi₂O₃/FEG first used as nitrogen reduction electrocatalyst exhibits excellent electrocatalysis performance and stability for nitrogen reduction reaction in neutral media.
- The superior electrocatalytic nitrogen reduction activity is attributed to the strong interaction of the Bi 6*p* band with the N 2*p* orbitals, binder-free nature of the electrodes, and facile electron transfer through the graphene nanosheets.

ABSTRACT Electrocatalytic nitrogen reduction reaction is a carbon-free and energy-saving strategy for efficient synthesis of ammonia under ambient conditions. Here, we report the synthesis of nanosized Bi₂O₃ particles grown on functionalized exfoliated graphene (Bi₂O₃/FEG) via a facile electrochemical deposition method. The obtained free-standing Bi₂O₃/FEG achieves a high Faradaic efficiency of 11.2% and a large NH₃ yield of 4.21 ± 0.14 μg_{NH₃} h⁻¹ cm⁻² at -0.5 V versus reversible hydrogen electrode in 0.1 M Na₂SO₄, better than that in the strong acidic and basic media. Benefiting from its strong interaction of Bi 6*p* band with the N 2*p* orbitals, binder-free characteristic, and facile electron transfer, Bi₂O₃/FEG achieves superior catalytic performance and excellent long-term stability as compared with most of the previous reported catalysts. This study is significant to design low-cost, high-efficient Bi-based electrocatalysts for electrochemical ammonia synthesis.

KEYWORDS N₂ reduction; Bi₂O₃ nanoplate; Electrocatalysis; Free-standing

Published online: 19 June 2020



SHANGHAI JIAO TONG UNIVERSITY PRESS

Springer

1 Introduction

Ammonia (NH_3) is considered to be a promising hydrogen energy carrier to alleviate the fossil fuel shortage and global climate change, for its high energy density, high hydrogen content, no carbon footprint and being easy to liquefy [1–3]. To date, the dominant method for industrial-scale NH_3 synthesis still depends on the traditional Haber–Bosch process [4–6]. However, this energy-intensive and environmentally hazardous process consumes 2% of the global annual energy and leads to 1% of the world's CO_2 emission [7]. It is thus imperative to develop sustainable and economical techniques for NH_3 synthesis at mild conditions.

The electrochemical nitrogen reduction reaction (ENRR) is regarded as an energy-saving and carbon-free process, which can synthesize NH_3 at ambient conditions by utilizing renewable energy such as those from wind and solar [8–12]. Unfortunately, the scaled-up application of the ENRR process is seriously hampered by the low ammonia yields and Faraday efficiency due to the extremely weak N_2 adsorption, the low solubility of N_2 in aqueous electrolytes, and the sluggish cleavage of the $\text{N}\equiv\text{N}$ bond [13]. Over the past 5 years, numerous metal-based materials, including metal [7, 14–18], metal oxides [19–21], metal sulfides [22, 23], metal nitrides [24], etc., have been developed as electrocatalysts for ENRR. Most of the above metal-based catalysts involving the metallic centers of Au [7], Ru [17], Ni [20], Mo [18, 22], etc., exhibited favorable activity for ENRR by elaborately designing the particle size, crystallinity, heteroatom doping, and/or vacancies. Despite the substantial progress, the ENRR still suffers from the major competitive hydrogen evolution reaction (HER). Therefore, the rational design of the active catalytic centers of efficient ENRR electrocatalysts that can efficiently reduce the large activation barrier of $\text{N}\equiv\text{N}$, accelerate its dissociation and most importantly suppress HER, is still a highly challenging but vitally important issue [25].

Bismuth-based catalysts are considered to be promising candidates for efficient ENRR in recent years [26–30]. Bi as a main group element with tunable p -electron density and intrinsic less reactive nature can selectively promote the reductive adsorption of N_2 to form N_2H^* without influencing the binding energy of the later intermediates, and also restrict the surface electron accessibility for effectively suppressing the competitive HER process [26–28]. Yan et al. demonstrated that overlapping of the Bi $6p$ bands and the

$2p$ orbitals of the N atom both below and above the Fermi level can offer a lower free-energy change for the potential-determining step and better ENRR activity than typical transition metal catalysts [29]. Most of the Bi-based electrocatalysts for ENRR reported previously are mainly focused on the metallic bismuth (Bi^0) [27–29]. It was reported that both the defect-rich Bi and 2D mosaic Bi nanosheets have been used for ENRR, and offered excellent selectivity in 0.2 M Na_2SO_4 (Faradaic efficiency (FE): 11.68% at -0.6 V vs. RHE) [28] and 0.1 M in Na_2SO_4 (FE: $10.46 \pm 1.45\%$ at -0.8 V vs. RHE) [31], respectively. As an abundant Bi-based material, Bi_2O_3 has received much attention in photocatalysis due to its unique electrical and optical properties [32–34]. It was also used as a precursor for the synthesis of other Bi-based materials [28]. However, bismuth oxide has hardly been reported for ENRR, with part of reason being that the semiconducting Bi_2O_3 shows poor charge transport, while the easy aggregation of Bi_2O_3 instead of nanosized status largely impairs the adsorption and reactivity to N_2 . Therefore, a robust support is necessary to enhance the conductivity, at the same time offer well dispersion of the Bi_2O_3 nanoparticles.

Functionalized exfoliated graphene (FEG) acts as an ideal 3D-conductive scaffold for supporting catalysts, which is constructed by ultrathin partially oxidized graphene nanosheets anchoring on the graphite substrate [35–37]. The FEG modified by oxygen-containing groups ($-\text{OH}$, $-\text{COOH}$) that provide active defect sites, can act as an excellent substrate for metal oxides deposition when using the metal ions as the precursor [38]. It is the high surface area and excellent electron conductivity of graphene nanosheets that can accelerate the charge transport and keep credible electric contact, resulting in the enormously improved catalytic efficiency [39–42]. In addition, polymer binder (e.g., Nafion) is widely used for attaching the electrocatalysts to the collectors, which seriously hampers the mass transport and obstructs the charge transmission, and therefore reduces the overall catalytic performance of the electrocatalysts [43, 44]. Therefore, the in situ growth of metal oxides on FEG with highly exposed active sites, superior electron conductivity, and large surface area is vitally important to improve the electrocatalytic performance. Based on the above analysis results, it is reasonable to assume that the composite electrocatalysts composed of well-coupled Bi_2O_3 and FEG can act as a promising candidate to promote the electrochemical reduction of N_2 to NH_3 .

Herein, we developed a new type of ENRR catalyst by immobilizing Bi_2O_3 nanoplates onto the surface of FEG, to form the free-standing hybrid material ($\text{Bi}_2\text{O}_3/\text{FEG}$), which was then directly used as an electrode for ENRR in different electrolytes under ambient conditions. In this ENRR system, the competitive hydrogen evolution reaction (HER) is expected to be suppressed by the better intrinsic ENRR activity of Bi. Moreover, the highly conductive FEG was utilized to compensate for the semiconducting property of Bi_2O_3 and eliminate its aggregation. The as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ catalyst exhibits high ENRR activity with a high NH_3 yield rate of $4.21 \pm 0.14 \mu\text{g}_{\text{NH}_3} \text{h}^{-1} \text{cm}^{-2}$, and a favorable FE as high as 11.2% at -0.5 V versus RHE in $0.1 \text{ M Na}_2\text{SO}_4$ electrolyte, out-performing most reported ENRR catalysts.

2 Experimental

2.1 Synthesis of the Functionalized Exfoliated Graphene (FEG)

The FEG substrate was prepared through an electrochemical exfoliation method according to our previous work with slight modification [45]. The exfoliation process was performed in a typical three-electrode cell using the graphite foil [GF, the exposed surface area is $1 \times 1 \text{ cm}^2$ (length \times width)] as the working electrode, a platinum plate and a saturated calomel electrode (SCE) as the counter and reference electrodes, respectively. First, the GF was scanned between 0.5 and 1.7 V (vs. SCE) using cyclic voltammetry at 15 mV s^{-1} in $0.5 \text{ M K}_2\text{CO}_3$ electrolyte for ten cycles. Subsequently, the electrode was further treated at a constant potential of 1.8 V (vs. SCE) for 2 h in 0.5 M KNO_3 aqueous solution to generate functional groups. Then, the electrode was potential dynamically scanned between -1.0 and 0.9 V (vs. SCE) at 50 mV s^{-1} for 50 cycles in 3 M KCl electrolyte to recover the electrical conductivity. Finally, the FEG substrate was rinsed with deionized water and ethanol to remove the residuals.

2.2 Synthesis of the nanosized Bi_2O_3 Modified FEG ($\text{Bi}_2\text{O}_3/\text{FEG}$)

$\text{Bi}_2\text{O}_3/\text{FEG}$ was synthesized through an electrochemical deposition process. 0.3 g of bismuth chloride (BiCl_3) was dissolved into 25 mL ethylene glycol (EG) and stirred at

$25 \text{ }^\circ\text{C}$ for 1 h forming the electrolyte. The electrodeposition process was conducted in a two-electrode cell with a platinum plate as the counter electrode and a piece of FEG ($1 \times 1 \text{ cm}^2$) as the working electrode. Bi_2O_3 nanoparticles were electrodeposited on FEG at a constant current density of 1 mA cm^{-2} at ambient temperature for 5 min . The as-synthesized product was washed with tetrahydrofuran and ethanol and subsequently dried in a vacuum oven at $70 \text{ }^\circ\text{C}$ for 12 h , finally obtaining free-standing $\text{Bi}_2\text{O}_3/\text{FEG}$.

2.3 Electrocatalytic ENRR Measurements

Before ENRR tests, the Nafion 117 membrane was cut into small pieces and then treated with $3 \text{ wt\% H}_2\text{O}_2$ water solution, deionized water, $1 \text{ mol L}^{-1} \text{ H}_2\text{SO}_4$ and deionized water for 1 h at $80 \text{ }^\circ\text{C}$, respectively. Finally, the obtained membrane was repeatedly rinsed until neutral pH was obtained and then was preserved in deionized water. Electrochemical measurements were performed in an airtight two-compartment cell at ambient conditions using an electrochemical workstation (CHI 760E), with $\text{Bi}_2\text{O}_3/\text{FEG}$ or FEG as the working electrode, Pt foil as the counter electrode, and Ag/AgCl (filled with 3.5 M KCl solution) as the reference electrode. The potentials were converted to reversible hydrogen electrode (RHE) scale via calibration with the Nernst equation ($E_{\text{RHE}} = E_{\text{Ag/AgCl}} + 0.059 \text{ pH} + 0.205 \text{ V}$). The linear sweep voltammetry (LSV) curves were collected in $0.1 \text{ M Na}_2\text{SO}_4$ electrolyte saturated with ultrahigh Ar or N_2 for 30 min at a sweep rate of 5 mV s^{-1} , respectively.

2.4 Determination of Ammonia

The concentrations of the synthesized NH_3 in the electrolyte were measured by a colorimetric method using Nessler's reagent as the color reagent. For this method, 10 mL electrolyte was mixed with 0.2 mL 50% seignette salt solution. Then 0.2 mL Nessler's reagent was added and the mixture was allowed still for 10 min . Then the mixture was detected as the absorbance at 420 nm by a UV-Vis spectrometer (Shimadzu UV-2600). A standard curve of the Nessler's reagent-based colorimetric method is constructed by measuring a series of absorbances for the reference solution with different NH_4Cl concentrations ($0.00, 0.10, 0.20, 0.30, 0.40,$ and $0.50 \mu\text{g mL}^{-1}$). The background is corrected with a blank solution (as shown in Fig. S1).

An ion-selective electrode meter (Orion Star A214 Bench-top pH/ISE Meter; Thermo Scientific) for NH_3 detection was also performed to further verify the reliability of the colorimetric method. The details were according to our previous work [46] (as shown in Supporting Information).

2.5 Determination of Hydrazine

The yield of hydrazine in the electrolyte was evaluated via Watt and Chrisp method. The hydrazine chromogenic reagent is a mixture of para-(dimethylamino) benzaldehyde (0.599 g), ethanol (300 mL) and concentrated HCl (30 mL). After 2 h ENRR reaction, 2 mL of the above reagent was added into 2 mL of the electrolyte and then the mixture was detected at 460 nm. The concentration-absorbance curve was calibrated using standard hydrazine hydrate solution with a series of concentrations ($Y = 2.225 X + 0.03$, $R^2 = 0.99913$) (as shown in Fig. S2).

2.6 Calculation of Faradaic Efficiency (FE) and NH_3 Yield Rate

The FE for NH_3 production and NH_3 yield rate were calculated at an applied potential as follow (Eqs. 1 and 2):


$$\text{FE}_{\text{NH}_3} = C_{\text{NH}_3} \times V \times 3F / Q \quad (1)$$

$$\text{NH}_3 \text{ yield rate} = C_{\text{NH}_3} \times V / (t \times m) \quad (2)$$

where C_{NH_3} is the concentration of NH_3 , V is the volume of the electrolyte, F is the Faraday constant of $96,485 \text{ C mol}^{-1}$, Q is the total charge passed through the electrochemical system, t is the reaction time of ENRR process, and m is the mass of the catalytic active site, i.e., the Bi atoms of Bi_2O_3 molecule on the surface of the $\text{Bi}_2\text{O}_3/\text{FEG}$ electrode.

2.7 Calculation of Equilibrium Potential

At the very beginning of the ENRR, the newly produced ammonia formed a type of coordination with water, as shown in Eq. 3:



The equilibrium potential for ENRR under our experimental conditions is calculated using the Nernst equation as shown in Eq. 4, assuming 1 atm of N_2 and an $\text{NH}_3 \cdot \text{H}_2\text{O}$ concentration of $0.5 \times 10^{-5} \text{ M}$ in the solution [46].


$$\begin{aligned} E &= E^\circ - \frac{RT}{nF} \ln \left(\frac{[\text{NH}_3 \cdot \text{H}_2\text{O}]^2}{[\text{H}^+]^6} \right) + 0.059 \text{ V} \times \text{pH} \\ &= 0.196 \text{ V (vs. RHE)} \end{aligned} \quad (4)$$

where $E^\circ = 0.092 \text{ V}$ is the standard potential for the above half reaction of ENRR, $R = 8.314 \text{ J mol}^{-1} \text{ K}^{-1}$ is the molar gas constant, $n = 6$ is the number of electrons transferred in Eq. 3, $F = 96,485 \text{ C mol}^{-1}$ is the Faraday constant, $T = 298.15 \text{ K}$ is the reaction temperature in this experimental condition.

3 Results and Discussion

3.1 Materials Characterization

Scheme 1 illustrates the synthesis procedure to obtain the free-standing $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid. Typically, the FEG substrate was prepared through electrochemical exfoliating the graphite foil into functionalized exfoliated graphene nanosheets with abundant oxygen functional groups. Sequentially, the Bi_2O_3 nanoplates were uniformly immobilized onto the FEG with BiCl_3 as the precursor through a facile electrochemical deposition method, during which



Scheme 1 Illustration of the synthesis of $\text{Bi}_2\text{O}_3/\text{FEG}$

the mass loading and the morphology of the Bi_2O_3 can be easily controlled by adjusting the electrolyte concentration and deposition duration. The actual weight of Bi in $\text{Bi}_2\text{O}_3/\text{FEG}$ electrodes was determined to be approximately 0.74 mg cm^{-2} by measuring the weight before and after the electrodeposition process, followed by ICP-AES confirmation.

The morphology and microstructure of as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ were investigated by scanning electron microscopy (SEM) and transmission electron microscopy (TEM). Figure 1a shows the SEM images of the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid. It can be clearly observed that, after electrochemical deposition, Bi_2O_3 nanoplates are uniformly grown on the surface of the loosely packed FEG layers. This is due to the fact that oxygen functional groups in graphene nanosheets play a structure-directing role in the electrochemical deposition. The Bi^{3+} precursors can be captured through coordination bonding with the hydroxyl and carboxyl groups in graphene nanosheets, which were introduced in the electrochemical exfoliation process [38]. Then this uniform deposition of Bi_2O_3 in the nanosheets of FEG can be achieved by the following electrochemical process. The SEM and corresponding elemental (Bi, C, and O) mapping images of $\text{Bi}_2\text{O}_3/\text{FEG}$ are shown in Fig. 1b. Uniform distribution of bismuth (from Bi_2O_3 nanoplates) combined with the carbon and oxygen can be detected over the whole area of the $\text{Bi}_2\text{O}_3/\text{FEG}$ nanosheet, further demonstrating the presence of homogeneous Bi_2O_3 nanoplates on the graphene sheet of FEG. The transmission electron microscopy (TEM) of the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid is shown in Fig. 1c, which further confirms the Bi_2O_3 nanoplates with a particle size of about 5 nm evenly decorated on the graphene nanosheets of FEG. The TEM image of $\text{Bi}_2\text{O}_3/\text{FEG}$ in Fig. 1c (inset) further displays that numerous Bi_2O_3 nanoplates are homogeneously dispersed on the surface of FEG. As shown in Fig. 1c, the high-resolution TEM (HRTEM) image of $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid reveals the uniform distributed Bi_2O_3 on the surface of FEG with well-defined nanocrystalline nature. The magnification corresponding HRTEM images in the circle area of Fig. 1c reveal the lattice fringes of 0.25 nm (Fig. 1d), which could be well indexed to the (102) plane of Bi_2O_3 . The selected area electron diffraction (SAED) pattern indicates the monocrystalline nature of Bi_2O_3 nanoplates and reveals the (102), (100), and (002) planes of Bi_2O_3 (inset of Fig. 1d), further confirming the existence of Bi_2O_3 in FEG.

X-ray diffraction (XRD) patterns of pure FEG and the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid are displayed in Fig. S3. The strong peak at 26.3° of FEG is indexed to the (002) plane of graphene [36] that confirms the successful synthesis of pure FEG. It is found that $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid also exhibited a characteristic peak of graphene at 26.6° . This intense and sharp peak indicates highly crystalline graphene nature of $\text{Bi}_2\text{O}_3/\text{FEG}$, which is beneficial to the electron transfer. No characteristic diffraction peaks of Bi_2O_3 are observed because of its lower loading content. This also implies the good dispersion of the very small Bi_2O_3 particles on the FEG.

The full-range X-ray photoelectron spectroscopy (XPS) spectra of FEG and the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid are shown in Fig. 1e, and it was observed that two peaks appeared at 285.6 and 532.0 eV, corresponding to the C 1s and O 1s core level spectrum, respectively. Moreover, the presence of Bi electrons was confirmed by the XPS analysis of $\text{Bi}_2\text{O}_3/\text{FEG}$, the three doublet peaks at around 690.0, 455.0, and 162.0 eV, corresponding to the Bi 4p, Bi 4d, and Bi 4f electrons, indicating that some Bi_2O_3 was immobilized on the FEG. In the high-resolution Bi 4f XPS spectrum (Fig. 1f), two main peaks centered at 159.8 and 165.1 eV can be identified as Bi 4f_{7/2} and Bi 4f_{5/2} signals of Bi^{3+} , respectively, in accordance with previous reports [47]. And the 0.8 eV blueshift of Bi 4f_{7/2} and Bi 4f_{5/2} peaks due to charge transfer from Bi^{3+} center to the FEG. The results from the above characterizations demonstrate that FEG is an excellent substrate for the deposition and fixation of Bi_2O_3 nanoplates. The incorporation of Bi_2O_3 nanoplates into the FEG prevented the aggregation of Bi_2O_3 nanoplates and provided more reactive sites, that may improve its performance of ENRR.

The contact angle measurement was then performed to investigate the hydrophilicity of FEG and $\text{Bi}_2\text{O}_3/\text{FEG}$. It can be seen from Fig. S4a, the surface of FEG whose contact angle is approximately 83° exhibits strong hydrophilicity, which is mainly due to the oxygen functional groups ($-\text{OOH}$ and $-\text{OH}$) of FEG. After decorated with Bi_2O_3 , the contact angle of the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ increases to around 110° (Fig. S4b), indicating a hydrophobic property. This hydrophobicity is expected to be helpful in promoting the ENRR performance by providing strong interaction with N_2 gas [48].




Fig. 1 **a** SEM images of $\text{Bi}_2\text{O}_3/\text{FEG}$ with the inset showing the high-magnification SEM image. **b** SEM and corresponding elemental (Bi, C, and O) mapping images of $\text{Bi}_2\text{O}_3/\text{FEG}$. **c** HRTEM images of $\text{Bi}_2\text{O}_3/\text{FEG}$, the inset shows the TEM image. **d** Corresponding HRTEM images in the circle area, the inset shows the SAED pattern. **e** XPS spectra of $\text{Bi}_2\text{O}_3/\text{FEG}$ and the FEG substrate; inset is the magnified image. **f** Bi 4f XPS spectrum of $\text{Bi}_2\text{O}_3/\text{FEG}$

3.2 Electrochemical Nitrogen Reduction

The ENRR performance of the prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ catalyst was evaluated in N_2 -saturated 0.1 M Na_2SO_4 electrolyte

under ambient conditions using a two-compartment electrochemical cell, separated by a Nafion 117 membrane. The free-standing $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid material was directly used as the working electrode, with a platinum plate as the

counter electrode and Ag/AgCl as the reference electrode (configuration shown in Fig. 2a). The feeding gas (ultra-high purity N_2 , 99.999%) was continuously bubbled into the cathode via a bubbler during the experiment at the flow rate of 10 mL min^{-1} . All potentials were reported on a reversible hydrogen electrode (RHE) scale. First, we studied the potential dependence of ENRR activity of Bi_2O_3/FEG by LSV in Ar- and N_2 -saturated $0.1 \text{ M Na}_2\text{SO}_4$ electrolytes at a scan rate of 5 mV s^{-1} . As shown in Fig. S5, the LSV curves of Bi_2O_3/FEG in Ar and N_2 -saturated electrolytes exhibit the same shape, but a higher current density is achieved in the N_2 -saturated electrolyte when potential is more negative than -0.4 V , implying that Bi_2O_3/FEG possesses catalytic activity for ENRR reaction.

Further, chronoamperometry tests at a series of potentials were carried out to explore the catalytic activity and identify the optimal potential of the Bi_2O_3/FEG electrode for the ENRR (Fig. 2b). The concentration of the produced

ammonia in solution after the 2 h electrolysis was determined independently by a spectrophotometry method with Nessler's reagent as a color reagent, while the possible N_2H_4 by-product was detected by a spectrophotometry method with $p\text{-C}_9\text{H}_{11}\text{NO}$ as an indicator.

The average ammonia yields and the corresponding FE of Bi_2O_3/FEG at potentials from -0.4 to -0.8 V (vs. RHE) in $0.1 \text{ M Na}_2\text{SO}_4$ are plotted in Fig. 2b. The FE value at -0.4 V (vs. RHE) is 7.1%, and then the ENRR rate and FE rise with the negative potential increasing until -0.5 V (vs. RHE), where the relatively high NH_3 yield and the maximum FE value can reach $4.21 \pm 0.14 \mu\text{g}_{NH_3} \text{ h}^{-1} \text{ cm}^{-2}$ (i.e., $5.68 \mu\text{g}_{NH_3} \text{ mg}_{Bi}^{-1} \text{ h}^{-1}$) and 11.2%, respectively. No N_2H_4 by-product has been detected, indicating the good selectivity of the Bi_2O_3/FEG catalyst for ENRR. Meanwhile, ENRR was also conducted on FEG in N_2 -saturated $0.1 \text{ M Na}_2\text{SO}_4$ solution at -0.5 V (vs. RHE) to verify the source of NH_3 . No NH_3 was detected, indicating that FEG had no catalytic




Fig. 2 a Schematic reaction cell for ENRR. b Faradic efficiency and NH_3 yield rate at various potentials in $0.1 \text{ M Na}_2\text{SO}_4$ electrolyte (determined by the Nessler's reagent). c Chronoamperometry results at the corresponding potentials. d FE and NH_3 yield rate at various potentials in $0.1 \text{ M Na}_2\text{SO}_4$ electrolyte (determined by ion-selective electrode meter)

activity toward ENRR for the production of NH_3 , and the contribution of NH_3 yield from the impurities of FEG was also negligible. Therefore, it can be inferred here that the Bi_2O_3 in $\text{Bi}_2\text{O}_3/\text{FEG}$ played a decisive role in the ENRR, while FEG possessed no activity toward the ENRR.

This ENRR catalytic performance of the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid material can even be comparable to the yields and efficiencies catalyzed by metal-based nanocatalysts as shown in Table S1. For example, Bi nanosheets (FE of 10.46% with an NH_3 yield rate of $2.54 \mu\text{g h}^{-1} \text{cm}^{-2}$ at -0.8 V (vs. RHE) in $0.1 \text{ M Na}_2\text{SO}_4$ electrolyte) [31] and Au nanorod (FE of 4.02% with an NH_3 yield rate of $1.648 \mu\text{g h}^{-1} \text{cm}^{-2}$ at -0.2 V vs. RHE in 0.1 M KOH electrolyte) [49]. The excellent ENRR performance of the as-prepared $\text{Bi}_2\text{O}_3/\text{FEG}$ hybrid material is mainly due to the following reasons. On the one hand, this high ENRR activity is primarily attributed to the Bi center from Bi_2O_3 , which can effectively inhibit the side reaction of HER during ENRR process by binding $^*\text{N}_2\text{H}$ more strongly without affecting the binding energy of $^*\text{NH}_2$ or $^*\text{NH}$ [26, 31], and offer a lower free-energy change than traditional transition metal for a better ENRR activity [29]. On the other hand, the nanosized Bi_2O_3 and the large surface of FEG, which provide abundant active sites, may insure the efficient ENRR reaction. Besides, the facile electron and mass transfer process from the graphene nanosheets of $\text{Bi}_2\text{O}_3/\text{FEG}$ accelerate the ENRR process through promoting the electron transport, and the hydrophobic property of $\text{Bi}_2\text{O}_3/\text{FEG}$ provides strong interaction with N_2 gas further accelerate the ENRR.

In addition, as shown in Fig. 2c, the current density at different potentials behaves good stability, which can be attributed to the well dispersion and anchoring of the nanosized Bi_2O_3 nanoplates on the graphene nanosheets. Unexpectedly, though the NH_3 yield reaches the highest average value of $5.8 \pm 0.15 \mu\text{g}_{\text{NH}_3} \text{h}^{-1} \text{cm}^{-2}$ at -0.8 V (vs. RHE), the FE values decrease obviously when the applied potentials are more negative than -0.5 V (vs. RHE). A plausible explanation is that the ENRR in this system was in a N_2 diffusion-controlled mode, and the feeding gas N_2 has extremely low solubility in aqueous electrolyte. At higher negative potentials, the competing reaction (HER) was dominant [46], so the surface of $\text{Bi}_2\text{O}_3/\text{FEG}$ was mainly occupied by the hydrogen molecules which would impede the mass transfer of N_2 to the surface of $\text{Bi}_2\text{O}_3/\text{FEG}$, and thus strongly reduce the ENRR selectivity.

The concentrations of the NH_3 synthesized by $\text{Bi}_2\text{O}_3/\text{FEG}$ at potentials from -0.4 to -0.8 V (vs. RHE) in $0.1 \text{ M Na}_2\text{SO}_4$ were also determined by ion-selective electrode meter to confirm the reliability of this colorimetric method for ammonia detection. As shown in Fig. 2d, the corresponding average NH_3 yields and FE were almost identical to that of determined by the Nessler's reagent (Fig. 2b) within experimental error, suggesting that it was reliable to use the Nessler's reagent for the quantitative analysis of the produced NH_3 .

Subsequently, chronoamperometry tests in N_2 -saturated 0.1 M KOH or $0.05 \text{ M H}_2\text{SO}_4$ electrolyte under the same experimental conditions as that of in Na_2SO_4 electrolyte were carried out to explore the catalytic activity of the $\text{Bi}_2\text{O}_3/\text{FEG}$ in strong basic and acidic media. As shown in Fig. 3a, the optimum average NH_3 yield rate $3.07 \pm 0.11 \mu\text{g}_{\text{NH}_3} \text{h}^{-1} \text{cm}^{-2}$ in the strong basic electrolyte occurred at -0.5 V (vs. RHE), indicating a wide pH response of $\text{Bi}_2\text{O}_3/\text{FEG}$. However, the relatively low FE of 0.59% may be caused by the high current density implying dominant HER (Fig. S7). Furthermore, the robust current stability of $\text{Bi}_2\text{O}_3/\text{FEG}$ in 0.1 M KOH has been confirmed for 2 h electrolysis, as shown in Fig. 3b, indicating ideal stability of $\text{Bi}_2\text{O}_3/\text{FEG}$ in the strong basic electrolyte. The NH_3 yields and the corresponding FE of $\text{Bi}_2\text{O}_3/\text{FEG}$ at potentials from -0.2 to -0.6 V (vs. RHE) in $0.05 \text{ M H}_2\text{SO}_4$ are plotted in Fig. 3c. The NH_3 yield at -0.2 V (vs. RHE) is $2.8 \mu\text{g}_{\text{NH}_3} \text{h}^{-1} \text{cm}^{-2}$ with the FE of 1.36%, then the NRR rate and FE decrease sharply with the potential shifted negatively. The dissatisfactory catalytic performance in $0.05 \text{ M Na}_2\text{SO}_4$ electrolyte should attribute to the instability of Bi_2O_3 and the drastic HER competing reaction in acid medium. Comparing the optimum FE and NH_3 yield rates of $\text{Bi}_2\text{O}_3/\text{FEG}$ in different electrolytes as shown in Fig. 3d, $\text{Bi}_2\text{O}_3/\text{FEG}$ exhibits excellent electrocatalysis performance and stability for ENRR in neutral media even better than that in strong basic and acidic media under the same ambient conditions. It is highly desired to develop electrocatalysts for efficient and durable ENRR catalysis at neutral conditions, which is beneficial for alleviating the serious environment sufferings, reducing equipment and catalyst corruptions, lower the cost of the whole ENRR process, and further accelerating the practical applications of ENRR.

The stability of the $\text{Bi}_2\text{O}_3/\text{FEG}$ was evaluated by consecutive recycling electrolysis and long-term




Fig. 3 a FE and NH₃ yield rate at various potentials in 0.1 M KOH electrolyte (determined by the Nessler's reagent). b Chronoamperometry results at the corresponding potentials. c FE and NH₃ yield rate at various potentials in 0.05 M H₂SO₄ electrolyte (determined by the Nessler's reagent). d Optimum FE and yield rates of NH₃ in different electrolytes (at -0.5 V vs. RHE, determined by the Nessler's reagent)

chronoamperometry test at -0.5 V (vs. RHE) in 0.1 M Na₂SO₄. As shown in Fig. 4a, no obvious change in the NH₃ yield and Faradaic efficiency could be observed during five consecutive recycling electrolysis, which suggests the excellent stability of Bi₂O₃/FEG for NH₃ synthesis at ambient conditions. In addition, slight degradation of current density in the process of long-term chronoamperometry test is detected for 12 h at -0.5 V (vs. RHE) (Fig. 4b). Moreover, no obvious variation of the NH₃ yield rate and FE could be observed after 12 h long-term chronoamperometry test, indicating the high robustness of Bi₂O₃/FEG toward ambient NH₃ synthesis. Furthermore, both the compositions and Bi₂O₃ nature of the Bi₂O₃/FEG could be well maintained after the long-term electrocatalysis reaction when comparing TEM images (Fig. 4c) and XPS (Fig. 4d) before and after the reaction. All these observations demonstrate the excellent electrochemical durability of the Bi₂O₃/FEG for the ENRR, which is another crucial factor for the enhancement of ENRR performances.

4 Conclusions

In summary, a highly efficient hybrid ENRR electrocatalyst composed of nanosized Bi₂O₃ supported on FEG was developed. Due to the synergistic effect between the nanosized Bi₂O₃ and the large surface area of FEG, the Bi₂O₃/FEG hybrid exhibited the superb electrocatalytic performance toward ENRR at a low overpotential of -0.5 V (vs. RHE) in the neutral electrolyte and under ambient temperature and pressure. The FE of Bi₂O₃/FEG in 0.1 M Na₂SO₄ electrolyte is 11.2% with the NH₃ yields of 5.68 μg_{NH₃} mg_{Bi}⁻¹ h⁻¹, which is superior to that of most state-of-the-art ENRR electrocatalysts reported up to date. The high ENRR activity is attributed to the Bi center from Bi₂O₃ during the ENRR process with the help of the facile electron transfer process from the graphene nanosheets of FEG. This work opens an avenue to rational designing of Bi-based carbon hybrid electrocatalysts and highlights the catalytic center engineering strategy to effectively manipulate the catalytic performance of electrocatalysts.




Fig. 4 **a** FE and NH₃ yield rates of Bi₂O₃/FEG calculated after consecutive recycling electrolysis in N₂-saturated 0.1 M K₂SO₄ solution at -0.5 V (vs. RHE) for 2 h. **b** 12 h durability test for Bi₂O₃/FEG toward ENRR at -0.5 V (vs. RHE), inset: the corresponding FE and NH₃ yield rate after durability test. **c** The HRTEM image of Bi₂O₃/FEG after ENRR. **d** Bi 4f XPS spectrum of Bi₂O₃/FEG after ENRR

Acknowledgements This work was financially supported by Liaoning Revitalization Talents Program—Pan Deng Scholars (XLYC1802005), Liaoning BaiQianWan Talents Program, the National Science Fund of Liaoning Province for Excellent Young Scholars, Science and Technology Innovative Talents Support Program of Shenyang (RC180166), Australian Research Council (ARC) through Discovery Early Career Researcher Award (DE150101306) and Linkage Project (LP160100927), Faculty of Science Strategic Investment Funding of University of Newcastle, and CSIRO Newcastl Energy Centre.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

Electronic supplementary material The online version of this article (<https://doi.org/10.1007/s40820-020-00444-y>) contains supplementary material, which is available to authorized users.

References

- Z.Q. Wang, K. Zheng, S.L. Liu, Z.C. Dai, Y. Xu, X.N. Li, H.J. Wang, L. Wang, Electrocatalytic nitrogen reduction to ammonia by Fe₂O₃ nanorod array on carbon cloth. *ACS Sustain. Chem. Eng.* **13**, 11754–11759 (2019). <https://doi.org/10.1021/acssuschemeng.9b01991>
- H. Cheng, L.X. Ding, G.F. Chen, L.L. Zhang, J. Xue, H.H. Wang, Nitrogen reduction reaction: molybdenum carbide nanodots enable efficient electrocatalytic nitrogen fixation under ambient conditions. *Adv. Mater.* **46**, 1870350 (2018). <https://doi.org/10.1002/adma.201870350>
- V. Rosca, M. Duca, M.T. de Groot, M.T.M. Koper, Nitrogen cycle electrocatalysis. *Chem. Rev.* **6**, 2209–2244 (2009). <https://doi.org/10.1021/cr8003696>
- C.D. Lv, C.S. Yan, G. Chen, Y. Ding, J.X. Sun, Y.S. Zhou, G.H. Yu, An amorphous noble-metal-free electrocatalyst that enables nitrogen fixation under ambient conditions. *Angew.*

- Chem. Int. Ed. **21**, 6073–6076 (2018). <https://doi.org/10.1002/anie.201801538>
5. C.J.M. Van der Ham, M.T.M. Koper, D.G.H. Hetterscheid, Challenges in reduction of dinitrogen by proton and electron transfer. *Chem. Soc. Rev.* **15**, 5183–5191 (2014). <https://doi.org/10.1039/C4CS00085D>
 6. H.V. Doan, H.A. Hamzah, P.K. Prabhakaran, C. Petrillo, V.P. Ting, Hierarchical metal–organic frameworks with macroporosity: synthesis, achievements, and challenges. *Nano-Micro Lett.* **11**, 54 (2019). <https://doi.org/10.1007/s40820-019-0286-9>
 7. H.J. Wang, H.J. Yu, Z.Q. Wang, Y.H. Li, Y. Xu, X.N. Li, H.R. Xue, L. Wang, Electrochemical fabrication of porous Au film on Ni foam for nitrogen reduction to ammonia. *Small* **6**, 1804769 (2019). <https://doi.org/10.1002/sml.201804769>
 8. G.F. Chen, X.R. Cao, S.Q. Wu, X.Y. Zeng, L.X. Ding, M. Zhu, H.H. Wang, Ammonia electrosynthesis with high selectivity under ambient conditions via a Li⁺ incorporation strategy. *J. Am. Chem. Soc.* **29**, 9771–9774 (2017). <https://doi.org/10.1021/jacs.7b04393>
 9. M.M. Shi, D. Bao, B.R. Wulan, Y.H. Li, Y.F. Zhang, J.M. Yan, Q. Jiang, Au sub-nanoclusters on TiO₂ toward highly efficient and selective electrocatalyst for N₂ conversion to NH₃ at ambient conditions. *Adv. Mater.* **17**, 1606550 (2017). <https://doi.org/10.1002/adma.201606550>
 10. M. Bat-Erdene, G.R. Xu, M. Batmunkh, A.S.R. Bati, J.J. White et al., Surface oxidized two-dimensional antimonene nanosheets for electrochemical ammonia synthesis under ambient conditions. *J. Mater. Chem. A* **9**, 4735–4739 (2020). <https://doi.org/10.1039/C9TA13485A>
 11. Y.F. Li, T.S. Li, X.J. Zhu, A.A. Alshehri, K.A. Alzahrani, S.Y. Lu, X.P. Sun, DyF₃: an efficient electrocatalyst for N₂ fixation to NH₃ under ambient conditions. *Chem. Asian J.* **4**, 487–489 (2020). <https://doi.org/10.1002/asia.201901624>
 12. M.G. Wu, J.Q. Liao, L.X. Yu, R.T. Lv, P. Li et al., 2020 Roadmap on carbon materials for energy storage and conversion. *Chem. Asian J.* **15**(7), 995–1013 (2020). <https://doi.org/10.1002/asia.201901802>
 13. X.H. Guo, Y.P. Zhu, T.Y. Ma, Lowering reaction temperature: electrochemical ammonia synthesis by coupling various electrolytes and catalysts. *J. Energy Chem.* **6**, 1107–1116 (2017). <https://doi.org/10.1016/j.jechem.2017.09.012>
 14. C.Y. Ling, X.W. Bai, Y.X. Ouyang, A.J. Du, J.L. Wang, Single molybdenum atom anchored on N-doped carbon as a promising electrocatalyst for nitrogen reduction into ammonia at ambient conditions. *J. Phys. Chem. C* **29**, 16842–16847 (2018). <https://doi.org/10.1021/acs.jpcc.8b05257>
 15. T.W. He, S.K. Matta, A.J. Du, Single tungsten atom supported on N-doped graphyne as a high-performance electrocatalyst for nitrogen fixation under ambient conditions. *Phys. Chem. Chem. Phys.* **3**, 1546–1551 (2019). <https://doi.org/10.1039/C8CP06978F>
 16. Y. Yao, H.J. Wang, X.Z. Yuan, H. Li, M.H. Shao, Electrochemical nitrogen reduction reaction on ruthenium. *ACS Energy Lett.* **6**, 1336–1341 (2019). <https://doi.org/10.1021/acsenergylett.9b00699>
 17. H.J. Wang, Y.H. Li, C.J. Li, K. Deng, Z.Q. Wang, Y. Xu, X.N. Li, H.R. Xue, L. Wang, One-pot synthesis of bi-metallic PdRu tripods as an efficient catalyst for electrocatalytic nitrogen reduction to ammonia. *J. Mater. Chem. A* **2**, 801–805 (2019). <https://doi.org/10.1039/C8TA09482A>
 18. D.S. Yang, T. Chen, Z.J. Wang, Electrochemical reduction of aqueous nitrogen (N₂) at a low overpotential on (110)-oriented Mo nanofilm. *J. Mater. Chem. A* **36**, 18967–18971 (2017). <https://doi.org/10.1039/C7TA06139K>
 19. H.T. Du, X.X. Guo, R.M. Kong, F.L. Qu, Cr₂O₃ nanofiber: a high-performance electrocatalyst toward artificial N₂ fixation to NH₃ under ambient conditions. *Chem. Commun.* **91**, 12848–12851 (2018). <https://doi.org/10.1039/C8CC07186A>
 20. K. Chu, Y.P. Liu, J. Wang, H. Zhang, NiO nanodots on graphene for efficient electrochemical N₂ reduction to NH₃. *ACS Appl. Energy Mater.* **3**, 2288–2295 (2019). <https://doi.org/10.1021/acsaem.9b00102>
 21. T. Xu, D.W. Ma, C.B. Li, Q. Liu, S.Y. Lu, A.M. Asiri, C. Yang, X.P. Sun, Ambient electrochemical NH₃ synthesis from N₂ and water enabled by ZrO₂ nanoparticles. *Chem. Commun.* **25**, 3673–3676 (2020). <https://doi.org/10.1039/C9CC10087C>
 22. X.H. Li, X. Ren, X.J. Liu, J.X. Zhao, X. Sun et al., A MoS₂ nanosheet–reduced graphene oxide hybrid: an efficient electrocatalyst for electrocatalytic N₂ reduction to NH₃ under ambient conditions. *J. Mater. Chem. A* **6**, 2524–2528 (2019). <https://doi.org/10.1039/C8TA10433F>
 23. P.X. Li, W.Z. Fu, P.Y. Zhuang, Y.D. Cao, C. Tang et al., Amorphous Sn/crystalline SnS₂ nanosheets via in situ electrochemical reduction methodology for highly efficient ambient N₂ fixation. *Small* **40**, 1902535 (2019). <https://doi.org/10.1002/sml.201902535>
 24. H.Y. Jin, L.Q. Li, X. Liu, C. Tang, W.J. Xu et al., Nitrogen vacancies on 2D layered W₂N₃: a stable and efficient active site for nitrogen reduction reaction. *Adv. Mater.* **32**, 1902709 (2019). <https://doi.org/10.1002/adma.201902709>
 25. G.F. Chen, S.Y. Ren, L.L. Zhang, H. Cheng, Y.R. Luo, K.H. Zhu, L.X. Ding, H.H. Wang, Nitrogen reduction reactions: advances in electrocatalytic N₂ reduction—strategies to tackle the selectivity challenge. *Small Methods* **6**, 1970016 (2019). <https://doi.org/10.1002/smt.201970016>
 26. J.H. Montoya, C. Tsai, A. Vojvodic, J.K. Nørskov, The challenge of electrochemical ammonia synthesis: a new perspective on the role of nitrogen scaling relations. *Chemsuschem* **13**, 2180–2186 (2015). <https://doi.org/10.1002/cssc.20150322>
 27. Z. Wang, F. Gong, L. Zhang, R. Wang, L. Ji et al., Electrocatalytic hydrogenation of N₂ to NH₃ by MnO: experimental and theoretical investigations. *Adv. Sci.* **1**, 1801182 (2019). <https://doi.org/10.1002/advs.201801182>
 28. Y. Wang, M.M. Shi, D. Bao, F.L. Meng, Q. Zhang et al., Generating defect-rich bismuth for enhancing the rate of nitrogen electroreduction to ammonia. *Angew. Chem. Int. Ed.* **28**, 9464–9469 (2019). <https://doi.org/10.1002/anie.201903969>
 29. Y.C. Hao, Y. Guo, L.W. Chen, M. Shu, X.Y. Wang et al., Promoting nitrogen electroreduction to ammonia with bismuth



- nanocrystals and potassium cations in water. *Nat. Catal.* **5**, 448–456 (2019). <https://doi.org/10.1038/s41929-019-0241-7>
30. F.Y. Wang, X. Lv, X.J. Zhu, J. Du, S.Y. Lu et al., Bi nanodendrites for efficient electrocatalytic N₂ fixation to NH₃ under ambient conditions. *Chem. Commun.* **14**, 2107–2110 (2020). <https://doi.org/10.1039/C9CC09803H>
 31. L.Q. Li, C. Tang, B.Q. Xia, H.Y. Jin, Y. Zheng, S.Z. Qiao, Two-dimensional mosaic bismuth nanosheets for highly selective ambient electrocatalytic nitrogen reduction. *ACS Catal.* **4**, 2902–2908 (2019). <https://doi.org/10.1021/acscatal.9b00366>
 32. Y. Peng, M. Yan, Q.G. Chen, C.M. Fan, H.Y. Zhou, A.W. Xu, Novel one-dimensional Bi₂O₃–Bi₂WO₆ p–n hierarchical heterojunction with enhanced photocatalytic activity. *J. Mater. Chem. A* **22**, 8517–8524 (2014). <https://doi.org/10.1039/C4TA00274A>
 33. H.J. Lu, Q. Hao, T. Chen, L.H. Zhang, D.M. Chen, C. Ma, W.Q. Yao, Y.F. Zhu, A high-performance Bi₂O₃/Bi₂SiO₅ p–n heterojunction photocatalyst induced by phase transition of Bi₂O₃. *Appl. Catal. B-Environ.* (2018). <https://doi.org/10.1016/j.apcatb.2018.05.069>
 34. S. Sanna, V. Esposito, J.W. Andreasen, J. Hjelm, W. Zhang et al., Enhancement of the chemical stability in confined δ-Bi₂O₃. *Nat. Mater.* **5**, 500–504 (2015). <https://doi.org/10.1038/nmat4266>
 35. Y. Song, X. Cai, X.X. Xu, X.X. Liu, Integration of nickel–cobalt double hydroxide nanosheets and polypyrrole films with functionalized partially exfoliated graphite for asymmetric supercapacitors with improved rate capability. *J. Mater. Chem. A* **28**, 14712–14720 (2015). <https://doi.org/10.1039/C5TA02810H>
 36. J.H. Cao, K.X. Wang, J.Y. Chen, C.J. Lei, B. Yang, Z.J. Li, L.C. Lei, Y. Hou, K. Ostrikov, Nitrogen-doped carbon-encased bimetallic selenide for high-performance water electrolysis. *Nano-Micro Lett.* **11**, 67 (2019). <https://doi.org/10.1007/s40820-019-0299-4>
 37. Y.L. Yang, Y. Tang, H.M. Jiang, Y.M. Chen, P.Y. Wan et al., 2020 Roadmap on gas-involved photo- and electro-catalysis. *Chin. Chem. Lett.* **12**, 2089–2109 (2019). <https://doi.org/10.1016/j.ccllet.2019.10.041>
 38. Y.W. Cheng, H.B. Zhang, C.V. Varanasi, J. Liu, Improving the performance of cobalt–nickel hydroxide-based self-supporting electrodes for supercapacitors using accumulative approaches. *Energy Environ. Sci.* **11**, 3314–3321 (2013). <https://doi.org/10.1039/C3EE41143E>
 39. D. Chen, L.H. Tang, J.H. Li, Graphene-based materials in electrochemistry. *Chem. Soc. Rev.* **8**, 3157–3180 (2010). <https://doi.org/10.1039/B923596E>
 40. S. Mukherjee, Z. Ren, G. Singh, Beyond graphene anode materials for emerging metal ion batteries and supercapacitors. *Nano-Micro Lett.* **10**, 70 (2018). <https://doi.org/10.1007/s40820-018-0224-2>
 41. Y. Sun, W. Zhang, J. Tong, Y. Zhang, S.Y. Wu et al., Significant enhancement of visible light photocatalytic activity of the hybrid B₁₂-PIL/rGO in the presence of Ru(bpy)₃²⁺ for DDT dehalogenation. *RSC Adv.* **31**, 19197–19204 (2017). <https://doi.org/10.1039/C7RA02062G>
 42. Y.L. Yang, M.G. Wu, X.W. Zhu, H. Xu, S. Ma et al., 2020 Roadmap on two-dimensional nanomaterials for environmental catalysis. *Chin. Chem. Lett.* **12**, 2065–2088 (2019). <https://doi.org/10.1016/j.ccllet.2019.11.001>
 43. Y.B. Xu, Y. Song, Z.G. Zhang, A binder-free fluidizable Mo/HZSM-5 catalyst for non-oxidative methane dehydroaromatization in a dual circulating fluidized bed reactor system. *Catal. Today* (2017). <https://doi.org/10.1016/j.cattod.2016.03.037>
 44. C.H. Jiang, Z.X. Ye, H.T. Ye, Z.M. Zou, Li₄Ti₅O₁₂@carbon cloth composite with improved mass loading achieved by a hierarchical polypyrrole interlayer assisted hydrothermal process for robust free-standing sodium storage. *Appl. Surf. Sci.* (2020). <https://doi.org/10.1016/j.apsusc.2019.144464>
 45. J.C. Liu, H. Li, M. Batmunkh, X. Xiao, Y. Sun, Q. Zhao, X. Liu, Z.H. Huang, T.Y. Ma, Structural engineering to maintain the superior capacitance of molybdenum oxides at ultrahigh mass loadings. *J. Mater. Chem. A* **41**, 23941–23948 (2019). <https://doi.org/10.1039/C9TA04835A>
 46. B. Yu, H. Li, J. White, S. Donne, J.B. Yi et al., Tuning the catalytic preference of ruthenium catalysts for nitrogen reduction by atomic dispersion. *Adv. Funct. Mater.* **6**, 1905665 (2020). <https://doi.org/10.1002/adfm.201905665>
 47. S.B. Liu, X.F. Lu, J. Xiao, X. Wang, X.W. Lou, Bi₂O₃ nanosheets grown on multi-channel carbon matrix to catalyze efficient CO₂ electroreduction to HCOOH. *Angew. Chem. Int. Ed.* **39**, 13828–13833 (2019). <https://doi.org/10.1002/anie.201907674>
 48. Q. Qin, M. Oschatz, Overcoming chemical inertness under ambient conditions: a critical view on recent developments in ammonia synthesis via electrochemical N₂ reduction by asking five questions. *ChemElectroChem* **4**, 878–889 (2020). <https://doi.org/10.1002/celec.201901970>
 49. D. Bao, Q. Zhang, F.L. Meng, H.X. Zhong, M.M. Shi et al., Electrochemical reduction of N₂ under ambient conditions for artificial N₂ fixation and renewable energy storage using N₂/NH₃ cycle. *Adv. Mater.* **3**, 1604799 (2017). <https://doi.org/10.1002/adma.201604799>